

RECEIVED
CENTRAL FAX CENTER

4230-101

JUN 26 2007

Section I (Amendments to the Claims)

Please amend claims 1 and 6, and cancel claims 4, 7, 23, and 24 as set out in the following listing of the claims of the application.

1. **(Currently amended)** An abrasive composed of an inorganic metal powder that contains titanium in an amount of at least one of not more than 1.5 wt% boron, not more than 0.1 wt% aluminum and not more than 0.1 wt% titanium and contains silicon in an amount of at least 0.8 wt%, is absent of boron and aluminum, and meets all the following conditions:
 - (1) its true specific gravity is 4 g/cm³ or more;
 - (2) its average particle diameter is from 5 µm to 50 µm inclusive;
 - (3) its maximum particle size is 100 µm or less; and
 - (4) its hardness (HNV) is from 110 to 340 inclusive; and [(,)]
 - (5) each particle of said powder has a substantially homogeneous composition throughout its volume

~~with the proviso that when the inorganic metal powder contains titanium in the absence of boron and aluminum, the inorganic metal powder further contains silicon in an amount of at least 0.8 wt%.~~
2. **(Previously presented)** The abrasive according to claim 1, wherein the average particle diameter of the inorganic metal powder is from 10 µm to 30 µm inclusive.
3. **(Previously presented)** The abrasive according to claim 1 or 2, wherein the maximum particle size of the inorganic metal powder is 80 µm or less.
4. **(Cancelled).**
5. **(Original)** The abrasive according to claim 4, wherein the principal component of the metal powder is iron or an iron-based alloy and the metal powder contains not more than 0.1 wt% aluminum and not more than 0.1 wt% titanium.

4230-101

6. **(Currently amended)** The abrasive according to claim 5, wherein the metal powder ~~[[is]]~~ comprises stainless steel containing not less than 8 wt% chromium.
7. **(Cancelled).**
8. **(Previously presented)** The abrasive according to claim 1, wherein the metal powder has a tap density in a range of from 4.3 g/cm³ to 4.8 g/cm³ inclusive.
9. **(Previously presented)** The abrasive according to claim 1, wherein 0.01 wt% to 5 wt% of a substance providing fluidity and resistance to moisture absorption is mixed in 100 wt% of the inorganic metal powder.
10. **(Previously presented)** The abrasive according to claim 1, wherein a substance providing fluidity and resistance to moisture absorption is attached to a part of or the entire surface of the inorganic metal powder in the proportions of 0.01 wt% to 5 wt% of the substance to 100 wt% of the inorganic metal powder.
11. **(Previously presented)** The abrasive according to claim 10, wherein the substance comprises a material selected from the group consisting of stearic acid and anhydrous silica.
12. **(Withdrawn)** An abrasive manufacturing method comprising the steps of:
 - causing molten inorganic metal contained in a tundish including an ejecting nozzle to eject from the ejecting nozzle, wherein the metal contains at least one of boron, aluminum and titanium, with the proviso that when the molten inorganic metal contains titanium in the absence of boron and aluminum, the molten inorganic metal further contains silicon in an amount of at least 0.7 wt%; and
 - ejecting a high-pressure fluid onto the molten metal ejected from the ejecting nozzle in such a manner that the high-pressure fluid will form a generally conical shape, which converges downwards, and will surround the molten metal, thereby powdering the molten metal;
 - wherein the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid is set between not less than 10 degrees and less than 30 degrees.

4230-101

13. **(Withdrawn)** The abrasive manufacturing method according to claim 12, wherein the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid is set from 15 degrees to 25 degrees inclusive.
14. **(Withdrawn)** The abrasive manufacturing method according to claim 12, wherein the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid is set to 20 degrees.
15. **(Withdrawn)** The abrasive manufacturing method according to any one of claims 12 to 15, further comprising the step of heating the tundish.
16. **(Withdrawn)** The abrasive manufacturing method according to claim 15, wherein the tundish is heated so that the temperature of the molten metal ejected from the ejecting nozzle will be between 1600 °C and 1700 °C inclusive.
17. **(Withdrawn)** The abrasive manufacturing method according to claim 12, wherein as the molten metal, a raw material is used whose principal component is iron or an iron-based alloy, and which contains carbon in the range of 0.060 wt% to 0.070 wt% inclusive, and to which no aluminum or titanium is added.
18. **(Withdrawn)** An abrasive manufacturing device comprising:
a tundish for containing molten metal;
an ejecting nozzle mounted on the tundish to cause the molten metal contained in the tundish to eject out; and
an atomizing nozzle for ejecting a high-pressure fluid onto the molten metal ejected from the ejecting nozzle in such a manner that the high-pressure fluid will form a generally conical shape, which converges downwards, and will surround the molten metal;
wherein the atomizing nozzle causes a high-pressure fluid to eject so that the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid will be between not less than 10 degrees and less than 30 degrees.

4230-101

19. **(Withdrawn)** The abrasive manufacturing device according to claim 18, wherein the atomizing nozzle causes the high-pressure fluid to eject so that the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid will be from 15 degrees to 25 degrees inclusive.

20. **(Withdrawn)** The abrasive manufacturing device according to claim 18, wherein the atomizing nozzle causes the high-pressure fluid to eject so that the angle of a vertex of the generally conical shape that is formed by ejection of the high-pressure fluid will be 20 degrees.

21. **(Withdrawn)** The abrasive manufacturing device according to any one of claims 18 to 20, further comprising a heater for heating the tundish.

22. **(Withdrawn)** The abrasive manufacturing device according to claim 21, wherein the heater heats the tundish so that the temperature of the molten metal ejected from the ejecting nozzle will be between 1600°C and 1700 °C inclusive.

23. **(Cancelled).**

24. **(Cancelled).**